

Meas. No. 3274 SOP 74 Date 20.03.2008 10:52:14 Operator: FRITSCHLAN\benes

Material: coal

p-6, 30min, 80ml steel+5x20mm

Description: in Wasser + Na4P2O7 + 30s Ultraschall

Calculation Automatische Modellerkennung

Mode Wet

Serial No. 22.2000.00/90771

Beam absorption 10.3 %

Pump 70.00 %

Meas. range 0.10 µm - 132.76 µm

Cellposition 2

Channels 102

Ultrasonic An

Scans 100

Prot.-No.: **080073**

5-99%

Obere Kornklasse [µm]	Q3(x) [%]
0.467	5.0
0.787	10.0
1.135	15.0
1.515	20.0
1.932	25.0
2.386	30.0
2.894	35.0
3.471	40.0
4.095	45.0
4.802	50.0
5.577	55.0
6.468	60.0
7.499	65.0
8.691	70.0
10.101	75.0
11.823	80.0
14.023	85.0
17.090	90.0
22.157	95.0
32.546	99.0

01-50µm

Obere Kornklasse [µm]	Q3(x) [%]
0.100	0.0
0.200	0.9
0.400	3.9
0.600	7.1
0.800	10.2
1.000	13.1
1.200	15.9
1.500	19.8
2.000	25.7
2.500	31.1
3.000	36.0
4.000	44.3
5.000	51.3
6.000	57.5
7.000	62.6
8.000	67.2
9.000	71.2
10.000	74.7
15.000	86.8
20.000	93.3
25.000	96.7
30.000	98.5
40.000	99.8
50.000	100.0

