

Meas. No. 3261 SOP 74 Date 19.03.2008 14:43:40 Operator: FRITSCHLAN\benes

Material: coal p-7, 25min, 45ml steel+7x15mm

Description: in Wasser + Na4P2O7 + 30s Ultraschall

Calculation Automatische Modellerkennung

Mode Wet Serial No. 22.2000.00/90771

Beam absorption 11.1 % Pump 70.00 %

Meas. range 0.10 µm - 132.76 µm Cellposition 2

Channels 102 Ultrasonic An

Scans 100 Prot.-No.: **080073**

5-99%

Obere Kornklasse [µm]	Q3(x) [%]
0.411	5.0
0.675	10.0
0.962	15.0
1.277	20.0
1.624	25.0
2.011	30.0
2.428	35.0
2.899	40.0
3.439	45.0
4.025	50.0
4.701	55.0
5.450	60.0
6.315	65.0
7.336	70.0
8.539	75.0
10.007	80.0
11.874	85.0
14.455	90.0
18.664	95.0
27.340	99.0

01-50µm

Obere Kornklasse [µm]	Q3(x) [%]
0.100	0.0
0.200	1.1
0.400	4.8
0.600	8.6
0.800	12.2
1.000	15.6
1.200	18.8
1.500	23.3
2.000	29.9
2.500	35.8
3.000	41.0
4.000	49.8
5.000	57.1
6.000	63.3
7.000	68.4
8.000	72.9
9.000	76.7
10.000	80.0
15.000	90.9
20.000	96.0
25.000	98.4
30.000	99.4
40.000	100.0
50.000	100.0

