

Meas. No. 6709 SOP 13 Date 21.04.2009 08:13:00 Operator: FRITSCHLAN\Benes

Material: **Coal** P7PL 1h 3mm

Description: Wasser + 0,1%Na4P2O7

Calculation Automatische Modellerkennung

Mode Wet Serial No. 22.2000.00/90771

Beam absorption 11,9 % Pump 65,00 %

Meas. range 0,10 µm - 265,52 µm Cellposition 2

Channels 102 Ultrasonic On

Scans 100 Prot.-No.: **090096**

5-99%

Obere Kornklasse [µm]	Q3(x) [%]
0,172	5,0
0,221	10,0
0,267	15,0
0,311	20,0
0,356	25,0
0,404	30,0
0,455	35,0
0,509	40,0
0,573	45,0
0,643	50,0
0,723	55,0
0,818	60,0
0,934	65,0
1,084	70,0
1,282	75,0
1,568	80,0
2,013	85,0
2,799	90,0
4,508	95,0
8,639	99,0

01-20µm

Obere Kornklasse [µm]	Q3(x) [%]
0,100	0,3
0,150	3,1
0,200	7,8
0,300	18,7
0,400	29,6
0,500	39,2
0,600	47,0
0,700	53,7
0,800	59,1
1,000	67,3
1,200	73,1
1,500	79,0
2,000	84,9
2,500	88,5
3,000	90,9
4,000	94,0
5,000	95,8
6,000	97,1
8,000	98,7
10,000	99,5
15,000	100,0
20,000	100,0

