

Meas. No. 7396 SOP 18 Date 17.08.2009 15:18:27 Operator: FRITSCHLAN\Benes

Material: **Cuprous Chloride**

P7pl 2mm 30min

Description: benzine (boiling point: 100-140°C)

Calculation Automatische Modellerkennung

Mode SVDU

Serial No. 22.2000.00/90771

Beam absorption 17,0 %

Pump 0,00 %

Meas. range 0,10 µm - 132,76 µm

Cellposition 2

Channels 102

Ultrasonic On

Scans 100

Prot.-No.: **090194**

5-99%

Obere Kornklasse [µm]	Q3(x) [%]
0,417	5,0
2,644	10,0
4,210	15,0
5,230	20,0
6,067	25,0
6,835	30,0
7,543	35,0
8,231	40,0
8,913	45,0
9,596	50,0
10,304	55,0
11,039	60,0
11,817	65,0
12,661	70,0
13,591	75,0
14,659	80,0
15,933	85,0
17,584	90,0
20,035	95,0
24,557	99,0

01-50µm

Obere Kornklasse [µm]	Q3(x) [%]
0,100	0,2
0,200	2,5
0,400	4,9
0,600	5,8
0,800	6,3
1,000	6,6
1,500	7,6
2,000	8,6
2,500	9,7
3,000	10,9
4,000	14,2
5,000	18,7
6,000	24,6
8,000	38,3
10,000	52,9
15,000	81,5
20,000	95,0
25,000	99,1
30,000	99,9
40,000	100,0
50,000	100,0

