

Meas. No. 7397    SOP 18    Date 17.08.2009 15:35:53    Operator: FRITSCHLAN\Benes

Material: **Cuprous Chloride**

**P7pl 5mm 30min**

Description: benzine (boiling point: 100-140°C)

Calculation Automatische Modellerkennung

Mode SVDU

Serial No. 22.2000.00/90771

Beam absorption 17,1 %

Pump 0,00 %

Meas. range 0,10 µm - 132,76 µm

Cellposition 2

Channels 102

Ultrasonic On

Scans 100

Prot.-No.: **090194**

5-99%

Obere Kornklasse [µm]	Q3(x) [%]
0,642	5,0
3,435	10,0
4,642	15,0
5,548	20,0
6,339	25,0
7,092	30,0
7,809	35,0
8,520	40,0
9,236	45,0
9,967	50,0
10,734	55,0
11,538	60,0
12,405	65,0
13,352	70,0
14,416	75,0
15,653	80,0
17,115	85,0
19,074	90,0
22,034	95,0
27,629	99,0

01-50µm

Obere Kornklasse [µm]	Q3(x) [%]
0,100	0,2
0,200	2,0
0,400	4,0
0,600	4,9
0,800	5,3
1,000	5,7
1,500	6,3
2,000	6,8
2,500	7,7
3,000	8,8
4,000	12,1
5,000	16,9
6,000	22,8
8,000	36,3
10,000	50,2
15,000	77,5
20,000	91,9
25,000	97,8
30,000	99,6
40,000	100,0
50,000	100,0

