

Meas. No. 7548    SOP 0    Date 10.09.2009 11:20:19    Operator: FRITSCHLAN\Benes

Material: **SiC mie broad**

**P7pl 0.6mm 2h**

Description: benzine (boiling point: 100-140°C)

Calculation Breit

Mode SVDU

Serial No. 22.2000.00/90771

Beam absorption 4,4 %

Pump 0,00 %

Meas. range 0,01 µm - 53,10 µm

Cellposition 1

Channels 108

Ultrasonic On

Scans 100

Prot.-No.: **090207**

5-99%

Obere Kornklasse [µm]	Q3(x) [%]
0,704	5,0
0,831	10,0
0,926	15,0
1,013	20,0
1,099	25,0
1,186	30,0
1,282	35,0
1,386	40,0
1,502	45,0
1,643	50,0
1,816	55,0
2,039	60,0
2,336	65,0
2,802	70,0
3,391	75,0
4,069	80,0
4,818	85,0
5,696	90,0
6,992	95,0
9,345	99,0

01-30µm

Obere Kornklasse [µm]	Q3(x) [%]
0,120	0,0
0,200	0,1
0,300	1,3
0,500	2,4
1,000	19,2
1,500	44,9
2,000	59,2
3,000	71,8
4,000	79,5
5,000	86,1
6,000	91,3
7,000	95,0
8,000	97,4
9,000	98,8
10,000	99,5
15,000	100,0
20,000	100,0
25,000	100,0
30,000	100,0

