

Meas. No. 7671 SOP 18 Date 22.09.2009 13:24:11 Operator: FRITSCHLAN\Benes

Material: **SiC**

P7pl WC 1,5mm 1h

Description: isopropylic alcohol

Calculation Automatische Modellerkennung

Mode SVDU

Serial No. 22.2000.00/90771

Beam absorption 12,4 %

Pump 0,00 %

Meas. range 0,10 µm - 53,10 µm

Cellposition 1

Channels 51

Ultrasonic On

Scans 100

Prot.-No.: **090207**

5-99%

Obere Kornklasse [µm]	Q3(x) [%]
0,124	5,0
0,146	10,0
0,169	15,0
0,193	20,0
0,217	25,0
0,243	30,0
0,272	35,0
0,302	40,0
0,336	45,0
0,375	50,0
0,417	55,0
0,465	60,0
0,520	65,0
0,583	70,0
0,660	75,0
0,756	80,0
0,880	85,0
1,055	90,0
1,356	95,0
2,029	99,0

001-5 µm

Obere Kornklasse [µm]	Q3(x) [%]
0,010	2,5
0,050	2,5
0,100	2,5
0,200	21,5
0,300	39,7
0,400	53,0
0,500	63,3
0,600	71,1
0,700	77,3
0,800	82,0
0,900	85,7
1,000	88,6
1,500	96,5
2,000	98,9
2,500	99,7
3,000	99,9
3,500	100,0
4,000	100,0
4,500	100,0
5,000	100,0

