

Meas. No. 7684 SOP 18 Date 24.09.2009 08:06:13 Operator: FRITSCHLAN\Benes

Material: **SiC**

P7pl WC 1,5mm 2h

Description: isopropylic alcohol

Calculation Automatische Modellerkennung

Mode SVDU

Serial No. 22.2000.00/90771

Beam absorption 9,9 %

Pump 0,00 %

Meas. range 0,10 µm - 53,10 µm

Cellposition 1

Channels 51

Ultrasonic On

Scans 100

Prot.-No.: **090207**

5-99%

Obere Kornklasse [µm]	Q3(x) [%]
0,172	5,0
0,213	10,0
0,249	15,0
0,286	20,0
0,324	25,0
0,365	30,0
0,407	35,0
0,452	40,0
0,500	45,0
0,552	50,0
0,611	55,0
0,676	60,0
0,750	65,0
0,835	70,0
0,935	75,0
1,058	80,0
1,218	85,0
1,440	90,0
1,814	95,0
2,632	99,0

001-5 µm

Obere Kornklasse [µm]	Q3(x) [%]
0,010	0,9
0,050	0,9
0,100	0,9
0,200	8,4
0,300	21,9
0,400	34,2
0,500	45,0
0,600	54,1
0,700	61,7
0,800	68,1
0,900	73,4
1,000	77,7
1,500	91,1
2,000	96,5
2,500	98,7
3,000	99,6
3,500	99,9
4,000	100,0
4,500	100,0
5,000	100,0

