

Meas. No. 8193 SOP 18 Date 18.11.2009 08:09:55 Operator: FRITSCHLAN\Benes

Material: **Microsilica**

P7pl WC 80ml IPA 1,6mm 60min

Description: in H2O + 0,1% Na4P2O7 (30s Ultrasonic)

Calculation Automatische Modellerkennung

Mode Wet

Serial No. 22.2000.00/90771

Beam absorption 11,7 %

Pump 60,00 %

Meas. range 0,10 µm - 53,10 µm

Cellposition 1

Channels 51

Ultrasonic On

Scans 100

Prot.-No.: **090271**

5-99%

Obere Kornklasse [µm]	Q3(x) [%]
0,257	5,0
0,362	10,0
0,469	15,0
0,585	20,0
0,712	25,0
0,858	30,0
1,023	35,0
1,216	40,0
1,440	45,0
1,703	50,0
2,019	55,0
2,407	60,0
2,871	65,0
3,429	70,0
4,128	75,0
5,013	80,0
6,174	85,0
7,753	90,0
10,274	95,0
15,197	99,0

01-30µm

Obere Kornklasse [µm]	Q3(x) [%]
0,120	0,2
0,200	2,5
0,300	7,1
0,500	16,4
1,000	34,3
1,500	46,3
2,000	54,7
3,000	66,2
4,000	74,2
5,000	79,9
6,000	84,3
7,000	87,8
8,000	90,6
9,000	92,8
10,000	94,6
15,000	98,9
20,000	99,9
25,000	100,0
30,000	100,0

