

Meas. No. 8097 SOP 18 Date 04.11.2009 15:34:48 Operator: FRITSCHLAN\Benes

Material: **Microsilica**

P7pl WC 80ml 0,6mm 30min

Description: in H2O + 0,1% Na4P2O7 (30s Ultrasonic)

Calculation Automatische Modellerkennung

Mode Wet

Serial No. 22.2000.00/90771

Beam absorption 6,2 %

Pump 60,00 %

Meas. range 0,10 µm - 53,10 µm

Cellposition 1

Channels 51

Ultrasonic On

Scans 100

Prot.-No.: **090271**

5-99%

Obere Kornklasse [µm]	Q3(x) [%]
0,144	5,0
0,191	10,0
0,243	15,0
0,303	20,0
0,375	25,0
0,457	30,0
0,554	35,0
0,671	40,0
0,810	45,0
0,982	50,0
1,191	55,0
1,452	60,0
1,777	65,0
2,174	70,0
2,703	75,0
3,348	80,0
4,196	85,0
5,378	90,0
7,276	95,0
11,038	99,0

01-20µm

Obere Kornklasse [µm]	Q3(x) [%]
0,100	1,5
0,150	5,7
0,200	10,9
0,300	19,8
0,400	26,6
0,500	32,3
0,600	37,0
0,700	41,1
0,800	44,7
1,000	50,5
1,200	55,2
1,500	60,9
2,000	67,9
2,500	73,2
3,000	77,4
4,000	84,1
5,000	88,6
6,000	92,0
8,000	96,2
10,000	98,4
15,000	99,9
20,000	100,0

