

Meas. No. 8099 SOP 18 Date 04.11.2009 15:46:56 Operator: FRITSCHLAN\Benes

Material: **Tuff**

P7pl WC 80ml 1,6mm 30min

Description: in H2O + 0,1% Na4P2O7 (30s Ultrasonic)

Calculation Automatische Modellerkennung

Mode Wet

Serial No. 22.2000.00/90771

Beam absorption 6,1 %

Pump 60,00 %

Meas. range 0,10 µm - 53,10 µm

Cellposition 1

Channels 51

Ultrasonic On

Scans 100

Prot.-No.: **090271**

5-99%

Obere Kornklasse [µm]	Q3(x) [%]
0,184	5,0
0,245	10,0
0,306	15,0
0,373	20,0
0,445	25,0
0,526	30,0
0,616	35,0
0,715	40,0
0,831	45,0
0,964	50,0
1,118	55,0
1,298	60,0
1,516	65,0
1,787	70,0
2,118	75,0
2,578	80,0
3,185	85,0
4,112	90,0
5,815	95,0
9,793	99,0

01-30µm

Obere Kornklasse [µm]	Q3(x) [%]
0,120	0,6
0,200	6,2
0,300	14,5
0,500	28,4
1,000	51,2
1,500	64,7
2,000	73,3
3,000	83,6
4,000	89,6
5,000	93,1
6,000	95,3
7,000	96,8
8,000	97,9
9,000	98,6
10,000	99,1
15,000	99,9
20,000	100,0
25,000	100,0
30,000	100,0

