

Meas. No. 8690 SOP 18 Date 19.01.2010 10:59:53 Operator: FRITSCHLAN\Benes

Material: **CeO2**

P7pl ZrO2 2mm 15min

Description: water + 0,1% Na4P2O7

Calculation Automatische Modellerkennung

Mode Wet

Serial No. 22.2000.00/90771

Beam absorption 15,0 %

Pump 65,00 %

Meas. range 0,10 µm - 53,10 µm

Cellposition 1

Channels 51

Ultrasonic On

Scans 100

Prot.-No.: **090386**

5-99%

Obere Kornklasse [µm]	Q3(x) [%]
0,192	5,0
0,242	10,0
0,288	15,0
0,335	20,0
0,383	25,0
0,433	30,0
0,487	35,0
0,544	40,0
0,608	45,0
0,678	50,0
0,756	55,0
0,846	60,0
0,951	65,0
1,075	70,0
1,228	75,0
1,421	80,0
1,679	85,0
2,073	90,0
2,807	95,0
4,751	99,0

01-20µm

Obere Kornklasse [µm]	Q3(x) [%]
0,100	0,5
0,150	1,7
0,200	5,7
0,300	16,3
0,400	26,7
0,500	36,2
0,600	44,4
0,700	51,5
0,800	57,6
1,000	67,1
1,200	74,2
1,500	81,8
2,000	89,2
2,500	93,3
3,000	95,8
4,000	98,2
5,000	99,2
6,000	99,6
8,000	99,9
10,000	100,0
15,000	100,0
20,000	100,0

