

**Meas.Nr.** 49028      **Date** Dienstag, 15 Mai 2012 02:43      **Personal Report No.:**  
**Material** Yellow Paste 2      P6cl 80ml Steel 1mm 15min      **M120102**  
**Description** dedisp. in EtOH; 30s ultrasonic LABORETTE 17

**Calculation** Fraunhofer      broad      **TradeOff** 1.000000e+002  
**Scans Fine** 100      **Scans Coarse** 0      **Channels** 51      **Beam Obscuration** 16.00 %  
**Meas. Range** 0.08 [ $\mu\text{m}$ ] - 42.30 [ $\mu\text{m}$ ]      **Pump** 6      **Ultrasonics** 0

%	< $\mu\text{m}$
5	0.13
<b>10</b>	<b>0.17</b>
15	0.22
20	0.26
25	0.31
30	0.36
40	0.45
<b>50</b>	<b>0.56</b>
60	0.69
70	0.84
80	1.05
<b>90</b>	<b>1.39</b>
95	1.70
98	2.08
99	2.33

%	< $\mu\text{m}$
2.3	0.1
13.0	0.2
44.5	0.5
53.2	0.6
67.4	0.8
77.7	1.0
85.2	1.2
92.2	1.5
96.0	1.8
97.6	2.0
99.5	2.5
99.9	3.0
100.0	3.5
100.0	4.0
100.0	5.0

