


Meas.Nr. 62232 **Date** Donnerstag, 14 März 2013 02:23 **Personal Report No.:**
Material Cement (pre crushed) 120s P6cl 250ml WC 20mm **M130049**
Description predisp. in water with 0,1% Na4P2O7 1min ultrasonic LABORETTE 17

Calculation Fraunhofer broad **TradeOff** 1.000000e+003
Scans Fine 100 **Scans Coarse** 100 **Channels** 102 **Beam Obscuration** 13.00 %
Meas. Range 0.08 [µm] - 2000.00 [µm] **Pump** 8 **Ultrasonics** 10

%	< µm
5	0.79
10	1.26
15	1.82
20	2.52
25	3.46
30	4.77
40	8.77
50	14.37
60	21.63
70	30.60
80	41.14
90	55.49
95	67.10
98	79.84
99	87.92

%	< µm
0.0	0.1
7.3	1.0
30.7	5.0
42.4	10.0
58.0	20.0
69.4	30.0
79.0	40.0
86.7	50.0
92.2	60.0
95.9	70.0
98.0	80.0
99.2	90.0
99.7	100.0
99.9	110.0
100.0	120.0



▲ 62232 dQ3(x) — 62232 Q3(x)