


Meas.Nr. 64657 **Date** Dienstag, 28 Mai 2013 10:17 **Personal Report No.:**
Material Exchange Resin Sample 2 30 min P6cl 20 mm steel **M130074**
Description predisp. 1min LABORETTE 17 ultrasonic

Calculation Fraunhofer broad **TradeOff** 1.000000e+003
Scans Fine 100 **Scans Coarse** 100 **Channels** 102 **Beam Obscuration** 15.00 %
Meas. Range 0.08 [µm] - 2000.00 [µm] **Pump** 7 **Ultrasonics** 10

%	< µm
5	1.15
10	1.50
15	1.83
20	2.16
25	2.52
30	2.93
40	3.99
50	5.67
60	8.47
70	12.34
80	17.09
90	23.90
95	29.70
98	36.18
99	40.35

%	< µm
0.0	0.1
0.3	0.5
3.2	1.0
17.7	2.0
46.6	5.0
64.2	10.0
75.9	15.0
84.9	20.0
91.2	25.0
95.2	30.0
97.6	35.0
98.9	40.0
99.6	45.0
99.9	50.0
100.0	60.0



▲ 64657 dQ3(x) — 64657 Q3(x)