

Meas.Nr. 64758 **Date** Mittwoch, 29 Mai 2013 01:40 **Personal Report No.:**
Material Exchange Resin Sample 2 90 min P6cl 5 mm steel **M130074**
Description predisp. 1min LABORETTE 17 ultrasonic

Calculation Fraunhofer broad **TradeOff** 1.000000e+003
Scans Fine 100 **Scans Coarse** 100 **Channels** 102 **Beam Obscuration** 14.00 %
Meas. Range 0.08 [µm] - 2000.00 [µm] **Pump** 7 **Ultrasonics** 10

%	< µm
5	0.87
10	1.13
15	1.36
20	1.57
25	1.78
30	2.00
40	2.46
50	3.00
60	3.66
70	4.53
80	5.83
90	8.26
95	10.75
98	13.79
99	15.83

%	< µm
0.1	0.1
1.2	0.5
7.4	1.0
30.0	2.0
50.0	3.0
64.3	4.0
80.9	6.0
89.2	8.0
93.8	10.0
96.5	12.0
98.7	15.0
99.8	20.0
100.0	30.0
100.0	40.0

