


**Meas.Nr.** 71495      **Date** Wednesday, 18 December 2013 12:33 PM      **Personal Report No.:**  
**Material** Zirconium oxide      10min P7pl 5 mm ZrO2      **M130307**  
**Description** predisp. in 0,1 % Na4P2O7 water. 1 min ultrasound LABORETTE 17

**Calculation** Fraunhofer      broad      **TradeOff** 1.000000e+003  
**Scans Fine** 100      **Scans Coarse** 100      **Channels** 102      **Beam Obscuration** 3.00 %  
**Meas. Range** 0.08 [µm] - 2000.00 [µm]      **Pump** 8      **Ultrasonics** 10

%	< µm
5	0.10
10	0.12
15	0.15
20	0.17
25	0.21
30	0.24
40	0.32
50	0.44
60	0.60
70	0.84
80	1.25
90	2.12
95	3.23
98	4.83
99	5.93

%	< µm
5.0	0.10
54.3	0.50
74.6	1.00
84.0	1.50
89.1	2.00
92.2	2.50
94.3	3.00
96.8	4.00
98.2	5.00
99.0	6.00
99.5	7.00
99.8	8.00
99.9	9.00
100.0	10.00



▲ 71495 dQ3(x)    — 71495 Q3(x)