

Meas.Nr. 71542 **Date** Wednesday, 18 December 2013 03:59 PM **Personal Report No.:**
Material Zirconium oxide 30min P7pl 5 mm ZrO2 **M130307**
Description predisp. in 0,1 % Na4P2O7 - 2 min Ultrasonic Bath LABORETTE 17

Calculation Fraunhofer broad **TradeOff** 1.000000e+002
Scans Fine 100 **Scans Coarse** 0 **Channels** 102 **Beam Obscuration** 13.00 %
Meas. Range 0.01 [µm] - 42.30 [µm] **Pump** 4 **Ultrasonics** 10

%	< µm
5	0.11
10	0.14
15	0.16
20	0.19
25	0.22
30	0.25
40	0.33
50	0.44
60	0.61
70	0.91
80	1.39
90	2.15
95	2.79
98	3.54
99	4.03

%	< µm
2.5	0.10
54.4	0.50
72.2	1.00
81.8	1.50
88.4	2.00
93.1	2.50
96.0	3.00
98.9	4.00
99.8	5.00
100.0	6.00
100.0	7.00
100.0	8.00
100.0	9.00
100.0	10.00

