


<b>Meas.Nr.</b>	71600	<b>Date</b>	Thursday, 19 December 2013 10:25 AM	<b>Personal Report No.:</b>	
<b>Material</b>	Porcelain		10min P5 350rpm 30 mm ZrO2	<b>M130348</b>	
<b>Description</b>	gemessen in Wasser + 0,1 % Na4P2O7 + 5 min Ultraschallbad LABORETTE 17 / dispersed in water + 0,1 % Na4P2O7 and 5 min ultrasonic bath LABORETTE 17				

---

<b>Calculation</b>	Fraunhofer	very_broad	<b>TradeOff</b>	1.000000e+005			
<b>Scans Fine</b>	100	<b>Scans Coarse</b>	100	<b>Channels</b>	102	<b>Beam Obscuration</b>	15.00 %
<b>Meas. Range</b>	0.08 [µm]	-	2000.00 [µm]	<b>Pump</b>	7	<b>Ultrasonics</b>	10

%	< µm
5	0.65
10	0.96
15	1.29
20	1.66
25	2.10
30	2.64
40	4.09
50	6.25
60	9.33
70	13.49
80	19.18
90	28.32
95	36.81
98	46.83
99	53.89

%	< µm
0.0	0.10
2.7	0.50
10.7	1.00
23.9	2.00
44.7	5.00
61.8	10.00
81.1	20.00
91.2	30.00
96.2	40.00
98.5	50.00
99.5	60.00
99.9	70.00
100.0	80.00
100.0	90.00
100.0	100.00



▲ 71600 dQ3(x) — 71600 Q3(x)