

Meas. No. 6721 SOP 45 Date 22.04.2009 08:02:55 Operator: FRITSCHLAN\Benes

Material: **Frit Glass L125**

**P7pr.I. 0,5mm 240min**

Description: water + 30s ultrasonic + 0.1% Na4P2O7

Calculation Automatische Modellerkennung

Mode Wet

Serial No. 22.2000.00/90771

Beam absorption 11,1 %

Pump 70,00 %

Meas. range 0,10 µm - 53,10 µm

Cellposition 1

Channels 51

Ultrasonic On

Scans 100

Prot.-No.: **090067**

5-99%

Obere Kornklasse [µm]	Q3(x) [%]
0,113	5,0
0,126	10,0
0,141	15,0
0,158	20,0
0,176	25,0
0,196	30,0
0,218	35,0
0,242	40,0
0,270	45,0
0,300	50,0
0,337	55,0
0,379	60,0
0,427	65,0
0,485	70,0
0,555	75,0
0,646	80,0
0,768	85,0
0,946	90,0
1,271	95,0
2,074	99,0

0.1-5µm (12 values)

Obere Kornklasse [µm]	Q3(x) [%]
0,100	5,2
0,300	49,9
0,500	71,1
1,000	91,1
1,500	96,9
2,000	98,8
2,500	99,6
3,000	99,8
3,500	99,9
4,000	100,0
4,500	100,0
5,000	100,0

