

Meas. No. 6651 SOP 45 Date 15.04.2009 11:04:08 Operator: FRITSCHLAN\Benes

Material: **Frit Glass L125** **3 mm 120 min**

Description: water + 0.1% Na4P2O7 + ultrasonic 30 sec

Calculation Automatische Modellerkennung

Mode Wet Serial No. 22.2000.00/90771

Beam absorption 12,5 % Pump 65,00 %

Meas. range 0,10 µm - 53,10 µm Cellposition 1

Channels 51 Ultrasonic On

Scans 100 Prot.-No.: **090067**

5-99%

Obere Kornklasse [µm]	Q3(x) [%]
0,171	5,0
0,324	10,0
0,462	15,0
0,583	20,0
0,697	25,0
0,811	30,0
0,927	35,0
1,046	40,0
1,172	45,0
1,305	50,0
1,450	55,0
1,608	60,0
1,784	65,0
1,980	70,0
2,205	75,0
2,493	80,0
2,839	85,0
3,309	90,0
4,048	95,0
5,639	99,0

01-10µm

Obere Kornklasse [µm]	Q3(x) [%]
0,100	1,5
0,200	6,0
0,300	9,2
0,400	12,6
0,500	16,5
0,700	25,1
1,000	38,1
1,500	56,7
2,000	70,5
2,500	80,1
3,000	86,9
4,000	94,8
5,000	98,0
6,000	99,3
7,000	99,8
8,000	100,0
9,000	100,0
10,000	100,0

